

### Product Description

KEG-2003H-50 A/B is a fast cure liquid silicone rubber for injection molding. It is supplied as two components which are mixed in a 1:1 ratio. The viscosity of KEG-2003H-50 A/B is low enough to allow easy pumping by common injection molding systems. Depending on the specific requirements, KEG-2003H-50 A/B can help to reduce costs of post-curing significantly due to low volatile content.

### Product Features

- Excellent mechanical properties
- Fast Curing
- Good Transparency
- Low content of volatile cyclics
- Easily Colourable
- No flash tendency
- Excellent material flow properties
- In accordance to EN 14350 "Volatile compounds content" (npc)

### Typical Applications

- Baby bottle nipples and applications requiring low volatiles.

### Packaging Information

20 kg pail kits and 200 kg drums

### Typical Properties

Type of HCR	LIMS
Viscosity A	1030
Viscosity B	1000
Durometer	51
Tensile Strength (psi)	1537
Elongation (%)	790
Specific Gravity	1.13
Tear Die B (ppi)	232
Press Cure/Post Cure	Press
Cure Time (minutes)	5
Cure Temp. (°C)	150
Cure Temp. (°F)	302

*Note: Values are not for specification purposes.*

### Storage and Shelf Life

Store in a cool, dry place.

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.